

# Technical Characteristics

STOPSOL											
Type Of Glass	Standard Thickness (mm)	Coating Position	Energy Characteristic				Light Characteristic		Solar Factor %	Shading Coefficient *3*4	U Value W/m2k
			Transmittance (%)	Reflectance (%)	Absorption (%)	Ultra Violet Transmission (%)	Transmittance (%)	Reflectance (%)			
Stopsol Supersilver Clear (SSFL)	6	#1	67	20	13	40	69	28	71	0.82	5.8
		#2	67	18	15	40	69	27	72	0.83	5.8
	8	#1	64	20	15	39	67	29	68	0.79	5.7
		#2	64	17	19	39	67	27	69	0.80	5.7
Stopsol Supersilver Dark Blue (SSDH)	5 (New)	#1	31	21	47	18	36	30	45	0.53	5.8
		#2	31	9	59	18	36	13	49	0.57	5.8
	6	#1	34	20	46	20	43	29	47	0.54	5.8
		#2	34	10	56	20	43	15	51	0.58	5.8
	8	#1	27	20	53	16	37	28	43	0.50	5.7
		#2	27	8	65	16	37	12	47	0.54	5.7
Stopsol Supersilver Blue Green (SSBN)	6	#1	31	19	50	16	48	27	46	0.53	5.8
		#2	31	9	60	16	48	16	49	0.56	5.8
	8	#1	25	18	57	12	44	26	43	0.49	5.7
		#2	25	8	67	12	44	13	46	0.53	5.7
Stopsol Supersilver Green (SSGN)	5	#1	35	18	47	14	56	27	46	0.53	5.8
		#2	35	11	54	14	56	20	49	0.56	5.8
	6	#1	31	18	50	13	54	27	46	0.53	5.8
		#2	31	10	59	13	54	19	49	0.56	5.8
	8	#1	24	18	58	7	49	26	42	0.48	5.7
		#2	24	8	68	7	49	15	45	0.52	5.7
Stopsol Supersilver Euro Grey (SSGE)	6	#1	39	20	41	15	33	28	51	0.58	5.8
		#2	39	9	53	15	33	10	54	0.62	5.8
	8	#1	31	18	50	9	26	26	46	0.53	5.7
		#2	31	7	62	9	26	7	50	0.58	5.7
Stopsol Supersilver Dark Grey (SSDG)	5	#1	30	21	49	29	15	29	45	0.51	5.9
		#2	30	7	63	29	15	6	49	0.56	5.9
Stopsol Classic Green (CGN)	5	#1	24	24	52	15	32	32	39	0.45	5.9
		#2	24	10	66	15	32	18	44	0.51	5.9
	6	#1	21	24	54	7	31	32	37	0.43	5.8
		#2	21	9	70	7	31	17	42	0.49	5.8
	8	#1	15	26	59	4	27	32	33	0.38	5.7
		#2	15	8	76	4	27	16	39	0.45	5.7
Stopsol Classic Dark Blue (CDH)	5	#1	26	26	48	11	26	33	40	0.46	5.8
		#2	26	10	64	11	26	16	45	0.52	5.8
	6	#1	23	25	53	10	24	31	38	0.44	5.8
		#2	23	10	67	10	24	14	43	0.50	5.8
	8	#1	18	25	57	8	20	31	35	0.40	5.8
		#2	18	8	74	8	20	11	40	0.46	5.8

**Remarks :**

- The data are calculated using spectral measurements that are confirm to standards NFRC 100 - 2010 and/or ISO/DIS 9050
- Energy properties according NFRC 100 - 2010 and/or ISO/DIS 9050
- U-Value (formerly k-value) is calculated according to standard NFRC 100 - 2010 and/or ISO/DIS 9050
- This document is no evaluation of the risk of glass breakage due to thermal stress. For tempered glass the risk of spontaneous breakage due to Nickel-Sulfide is not covered bt PT Asahimas Flat Glass Tbk. The Heat Soak test is available on request
- Specifications, technical and other data are based on information available at the time of preparation of this document and are subject to change without notice. PT Asahimas Flat Glass Tbk can not held responsible for any deviation between the data introduced and the conditions on site